

# STATIC R44 11

Excellent static rope. Type A rope – low stretch kernmantel rope designed for general use in rope access (including all kinds of work positioning and restraint), in rescue and in caving.

#### **DESCRIPTION**

Designed for rope access, positioning, rescue or rigging.

Meets the most demanding requirements of rescue specialists, firefighters, workers at height and all other professionals who require the highest quality in their daily operations.

Pack:

30–80, 100 m


**Spool:** 100, 200 m

#### **COLORS**

L0450VO orange L0450WG white L0450RR red L0450BB black

(note: product code for rope on

spool L0451\*)



## **STANDARDS**

# **C**€ 1019

EN 1891





### **FEATURES**



11 mm



34.9 kN



77 g/m



unique number



warranty

#### **MATERIALS**




■ **100** % PAD

#### **TECHNICAL DATA**

strength	34.9 kN	-2 kN
knot breaking force	22.3 kN	-2 kN
stitched eye breaking force	28.5 kN	-2 kN
strength with termination	15 kN/3 min	
elongation	3.2 %	±1%
number of falls	>20	
weight	77 g/m	±l g/m
sheath slippage	0 %	±3 %
shrinkage	1%	±1%
mass of the core /outer sheath	62 % / 38 %	±2 %
knotability	0.7	±0,1
diameter	11.0 mm	±0,2 mm
impact force	5.6 kN	±0,3 kN
material	PA	



#### **TECHNICAL DATA**



#### **COMPARISON**


#### STATICR4411-STATIC11

- The sheath made on 44 carrier machine better corresponds to 11 mm diameter of the rope and thus the core/sheath ratio is ideal with reference to the strength of the rope and strength of the rope with knots.
- At the same time the sheath on R44 ropes is braided more densely having positive results:
  - better protection of the core against dirt and dust,
  - lower risk of core prolapse through the sheath when bent over small diameters,
  - smoother running through belay/rappel devices.



#### **MAINTENANCE**

Lifetime of this product depends on the frequency and the environment (salt, sand, moisture, chemicals, etc.) in which is used. Without taking wear or mechanical damage into account and in compliance with the conditions specified in the instructions for use this product may be used 15 years from the date of production and 10 years from the date of the first use.





beware





of salt









drying

instructions

















 $80\,g/m$ 

white, red, black



L0430 10.5 mm 31.5 kN 72 g/m khaki, white, red, black

**STATIC R44 10.5**